AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240. North Melbourne. Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: **Hunter Douglas Limited**

> 338 Victoria Road Rydalmere NSW 2116

15-002622 Test Number :

Issue Date 18/06/2015 **Print Date** 18/06/2015

"Madison Two" **Sample Description** Clients Ref:

Woven coated/Backcoated fabric

Colour: Alaska/White End Use:

Nominal Composition:

Blinds

Base Cloth: Polyester, Coating: Acrylic

435g/m2 Nominal Mass per Unit Area/Density:

Nominal Thickness: 0.51mm

AS 1530.2-1993

Methods for fire tests on building materials, components and structures.

Part 2: Test for flammability of materials

Date Tested		18/06/2015	
Flammability Index		63	
	Length	Width	
Spread Factor	40	40	
Speed Factor	43	42	
Heat Factor	20	20	
Maximum baight (d)			
Maximum height (d)			
Mean	21.0	21.0	
Coefficient of Variation	0.0	0.0	%
Time			
Mean	46.6	48.8	sec
Coefficient of Variation	9.1	6.1	%
Heat (a)			
Mean	81.6	85.0	°C.min
Coefficient of Variation	4.7	3.5	%
Number of Specimens Tested	6	6	

27208 5308 Page 1 of 2



Accredited for compliance with ISO/IEC 17025

Chemical Testing - Mechanical Testino

Performance & Approvals Testing

Accreditation No Accreditation No. : Accreditation No 983 985

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertise the Managing Director of AWTA Ltd.





IAEL A. JACKSON B.Sc.(Hons)

Australian Wool testing Authority Ltd Copyright - All Rights Reserved