

AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Textile Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : VERTILUX PTY LTD
PO BOX 611
TULLAMARINE VIC 3043

TEST NUMBER : 7-550521-BV
DATE : 19/02/2007
ORDER NUMBER : 60130

SAMPLE DESCRIPTION Clients ref: "Zing blackout ref: 33983"
Cream woven fabric - coated
Nom: 100% polyester face
acrylic based coating 420g/m2
Enduse: blinds / screens

AS/NZS 3837:1998 Method of Test for Heat and Smoke Release Rates
for Materials and Products Using an Oxygen
Consumption Calorimeter

Results:-

	1	Specimen 2	3	Mean	
Average Release Rate	43.7	49.4	53.4	48.8	kW/m2
Average Specific extinction area (according to Specification C1.10 of the Building Code of Australia)	199.2	188.4	365.6	251.1	m2/kg

BCA Classification:-
Group Classification 2 2 2
(according to Specification A2.4 of the Building Code of Australia)

158430

1

(CONTINUED NEXT PAGE)

PAGE 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

