

EXCLUSIVE TO **vertilux** STATUS 10%™ Transparent

Why STATUS 10%™ Transparent?

Status is a Basketweave 2 x 2 woven construction that allows insulation from harmful UV rays with heat and reflection properties that assist in maintaining an energy efficient environment. There are a range of stylish tonal colours to select from. Suitable for use on the Vertilux Roller Blind and Panel Glide Systems.

Colour Range



Fabric Specifications

Quality:	30% Polyester/70% PVC (100% Free of Formaldehyde, Heavy Metal and Phthalate to help reduce toxins in your environment)
Width:	Maximum Roller Width 3000mm Maximum Roman Width 2930mm
Weave & Opacity:	Basketweave 2x2 woven to achieve transparent opacity.
Weight:	10% - 370 gr/m ² ± 5%
Thickness	10% - 0.55mm ± 5%
Humid Room Suitability:	This fabric is suitable for use in humid rooms, such as bathrooms.
Printing:	Suitable for screen printing. Ask for more details.
Fire Classifications:	AWTA AS1530.2 1993 AWTA AS1530.3 1999 AWTA AS3837 1998 German Standard: DIN 4102 - B1
Oeko-Tex Certified:	Yes
Lightfastness:	Tested BS EN ISO 105:B02: 1999 Blue scale rating 8+ Fabric with a 5+ result offers excellent resistance to the fading effect of light.
VOC test:	US EPA 5021
Anti Fungal:	Tested to standard BS EN ISO 846: 1997 Method A to ensure that the fabric inhibits mould.
Fabric Warranty:	5 years (internal use only)
Care Instructions:	Do not allow dust to accumulate. Gently vacuum with appropriate attachment. Do not dry clean. Test in an inconspicuous area with mild detergent solution before spot cleaning. When spot cleaning do not allow that area to become fully wet, use damp cloth only.


Light and Solar Optical Properties
Independently tested to ASHRAE 74-1988

	Ts	Rs	As	Tv/Vlt	Rl	Al	Tuv	O-F	Shading Coefficient			G-Value		
									3mm Cl.	6mm Cl.	6mm H.A.	3mm Cl.	6mm Cl.	6mm H.A.
GLACIER 10%	38	55	7	36	46	18	13	12	0.47	0.46	0.39	0.41	0.40	0.34
MAGNOLIA 10%	26	60	14	24	55	21	10	11	0.40	0.40	0.35	0.35	0.35	0.30
CORNSILK 10%	26	52	22	24	50	26	10	11	0.46	0.45	0.38	0.40	0.39	0.33
LIMESTONE 10%	21	55	24	22	43	35	12	11	0.43	0.42	0.36	0.37	0.36	0.32
MARBLE 10%	18	42	40	19	40	41	10	11	0.51	0.49	0.40	0.44	0.42	0.35
MISTRAL 10%	18	38	38	19	38	42	10	11	0.55	0.52	0.41	0.47	0.44	0.36
OATMEAL 10%	21	35	44	21	31	48	11	11	0.57	0.54	0.43	0.50	0.47	0.37
FOG 10%	14	28	58	16	25	59	10	10	0.60	0.57	0.44	0.52	0.50	0.38
BASALT 10%	12	13	75	16	13	71	11	11	0.69	0.66	0.49	0.60	0.57	0.43
CARBON 10%	12	13	75	16	10	74	10	11	0.70	0.66	0.49	0.61	0.57	0.43
GRAPHNEL 10%	12	8	80	17	7	76	11	12	0.73	0.69	0.50	0.63	0.60	0.44
PITCH 10%	10	4	86	14	4	82	10	10	0.75	0.71	0.52	0.65	0.62	0.45
COPPER 10%	11	6	83	15	6	59	10	10	0.74	0.70	0.51	0.64	0.61	0.44

Independently tested to ASHRAE 74-1988

Legend to Light and Solar Optical Properties abbreviations:

- Ts: Solar Transmittance (%) As: Solar Absorbance (%) Rl: Light Reflectance (%) Tuv: Ultraviolet Transmittance (%)
- Rs: Solar Reflectance (%) Tv/Vlt: Visible Light Transmittance (%) Al: Light Absorbance (%) O-F: Openness Factor



BLINDS PROUDLY MADE IN AUSTRALIA

vertilux.com.au